

TIANKI (CHINA) ENTERPRISE CO., LTD.



Plant:Nanyang ETDZ, Xiaoshan District Hangzhou China

Tel:+86-571-82778679 Fax:+86-571-82778609 Email:sales@tkechem.com

TECHNICAL DATA SHEET

Product Description:

Product Name: Middle chrome yellow (factory standard)

Color Index: Pigment Yellow 34

CAS No. 7758-97-6

Application:

Recommend: Coating,Paint,ink

Physical Properties

Tinting Strength(Compared with standard),%≥	97
Volatile Matter at 105 ⁰ C(% _{m/m})≤	1
Soluble Matter In Water,%≤	1
Alkalinity and Acidity of Aqueous Extract,ml≤	20
PH Value Of Water Slurry	5~8
Oil Absorption, g/100g≤	17
Residues On Sieve(45μm mesh sieve),%(_{m/m}) ≤	0.5
Ease Of Dispersion,μm≤	25
Heat Resistance, °C	220
Light Fastness,(Grade)≥	6
Total Lead Content,%(_{m/m}) ≥	50
Lead Chromate Content, %(_{m/m}) ≥	90

Note: The above information is provided as guidelines for your reference only. The accurate effects should base on the test results in laboratory.