

TIANKI (CHINA) ENTERPRISE CO., LTD.



Plant: Nanyang ETDZ, Xiaoshan District Hangzhou China

Tel: +86-571-82778679 Fax: +86-571-82778609 Email: sales@tkechem.com

TECHNICAL DATA SHEET

Product Description:

Product Name:	Lithol Fast Yellow G
Color Index:	Pigment Yellow 139
C.I.No.	56298
CAS No.	36888-99-0
EC No.	253-256-2
Chemical Nature:	Disazo
Chemical Formula	C ₁₆ H ₉ N ₅ O ₆

Technical Properties:

a reddish yellow pigment, Semi-transparent with with excellent kind properties and high luster, high color strength.

Application:

Recommend: inks, paints, coatings, High grade Plastics resins, textile printing, plastic products etc.

Physical Properties

Density(g/cm ³)	1.74
Moisture (%)	≤1.5
Water Soluble Matter	≤1.0
Oil Absorption (ml / 100g)	45-69
Electric conductivity (us/cm)	≤500
Fineness(80mesh)	≤5.0
PH value	5.0-6.0

Fastness Properties (5=Excellent, 1=Poor)

Acid Resistance	5	Soap Resistance	-
Alkali Resistance	5	Bleeding Resistance	5
Alcohol Resistance	5	Migration Resistance	-
Ester Resistance	5	Heat Resistance (°C)	280
Benzene Resistance	5	Light	8
Ketone Resistance	-	Fastness(8=Excellent)	

Note: The above information is provided as guidelines for your reference only. The accurate effects should base on the test results in laboratory.